

**Indication**

Cavex Cream Alginate features superior water absorption and fast viscosity built-up. This results in very easy mixing and the formation of an extreme smooth and creamy consistency. The Cavex Cream Alginate has an attractive combination of purple colour and bubble gum flavour. Cavex Cream Alginate is suitable both for general dental practice and for orthodontics.

**Storing Cavex Cream Alginate**

- Always store Cavex Cream Alginate in a cool, dry place.
- After opening the packaging store Cavex Cream Alginate in a firmly closed storage box. Always close the box immediately after using the material.

**Dosing**

- Stir the powder to loosen it well.
- Scoop it from the storage box with a light, swift movement and then stroke the powder smooth: do not compress the powder in the scoop.
- Mix water (at room temperature) and powder in the mixing cup.
  - \* for a partial impression                      1 scoop    +    1/3 beaker of water
  - \* for a full impression                            2 scoops   +    2/3 beaker of water
  - \* for an extra-large impression                3 scoops   +    full beaker of water
  - \* for stiff alginate **(1)**                            3 scoops   +    water (high viscosity level)

*Ideal mixing ratio: 21.2 g = 3 measuring scoops: 46 ml = 1 full beaker.*

*You can make the mixture thinner or thicker by adding more or less water respectively.*

**(1)Cavex stiff alginate technique**

The impression technique to make an accurate first (functional) impression for a stable denture. It is the combination of an impression tray with rimlock for edentulous jaws e.g. Schreinemakers' full denture tray system" and stiff (high viscosity) Cavex alginate. Stiff alginate is the normal amount of powder with 30% less water. The high viscosity alginate pushes the soft tissue aside. As a result the anatomical details, even the frenae are clearly visible. The gypsum model can be lined-out accurately and fully, which enables the dental technician to ensure that the individual tray is a perfect fit. The result: a stable denture and satisfied patient.

**Mixing**

- Mix both components together carefully and thoroughly for 20 - 30 seconds until a smooth and homogeneous mixture is obtained.
- Fill the tray immediately and use a wetted finger to stroke it smooth.
- Make sure that the patient has rinsed the mouth with warm water in the mean time.

**Taking the impression**

- Within 1 minute (fast set) 1½ minute (normal set) after mixing, insert the filled impression tray into the patient's mouth applying gentle pressure.
- Allow the impression material to set in the mouth for 1½ minute (fast & normal set).
- Remove the tray from the mouth in a single rapid movement.
- Rinse the tray under cold running water to remove saliva and any residues.
- Remove any excess water, but leave the surface moist. Never blow-dry!

**Making the plaster models**

- Immediately after rinsing, pour out the plaster impression and make a second plaster model if desired.
- If immediate pouring is impossible: store the impression in a firmly sealed plastic bag and add a few drops of water to achieve a relative humidity of 100%. This is essential for optimum results at a later pouring.
- Make the plaster model within 48 hours after taking the impression.

For preference, use one of the following plaster products:

Type 3: Moldano® (Heraeus Kulzer)

Type 4: Moldastone®, Moldasynt® (Heraeus Kulzer)

### Product specifications

Cavex Cream Alginate meets the ISO 21563 and ADA 18 standards.

	ISO 21563*	Fast	Normal	
Powder / water ratio	-	21.2 / 46	21.2 / 46	g / ml
Mixing time	< 60	20	30	sec.
Total working time according to manufacturer's indication		1.20	2.00	min.
Total setting time acc. manufacturer's indication		2.20	3.30	min.
Compression strength	> 0.35	>1.0	>1.0	MPa
Recovery after distortion	> 95	>96	>96	%
Elastic distortion	5-20	14-16	14-16	%
Detail reproduction	50	5	5	µm

\* measured with deionised water at 23°C

### Mixing scheme Cavex Cream Alginate

	Mixing	filling + placing	Setting in mouth
Fast Set	20 sec.	1 minute	1 minute
Normal Set	30 sec.	1 minute 30 sec.	1 minute 30 sec.
Total working time			
Fast Set	1 minute 20 sec		
Normal Set	2 minutes		
Total setting time			
Fast Set	2 minutes 20 sec.		
Normal Set	3 minutes 30 sec.		

Note.

1. The working/setting times increase with a lower (water) temperature. At higher temperatures the times become shorter.
2. The water hardness has the same effect: the harder the water used for mixing, the shorter the working/setting time.

Our technical advice, whether verbal, in writing or by way of trials, is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended processes and uses.

The application, use and processing of the products are beyond our control and, therefore, entirely your own responsibility. Should, in spite of this liability be established for any damage, it will be limited to the value of the goods delivered by us and used by you. We will, of course, provide consistent quality of our products within the scope of our General Conditions of Sale and Delivery.