DDcontrast® firing paste

Eigenschaften:

DD contrast® firing paste – die ultimative Keramikbrennpaste zur Objektfixierung

- Stabilisiert selbst schwierige Keramikarbeiten beim Brennvorgang.
- Rückstandslos entfernbar – ein Druckluftstoß reicht.
- Kein lästiges Herauskratzen oder Sandstrahlen nach dem Brennvorgang.
- Keine Trocknungszeit.

Bedienungshinweise:

Platzieren Sie eine kleine Menge direkt aus der Spritze im Inneren der Krone bzw. auf der rückseitigen Fläche von Veneers und Inlays. Bitte beachten Sie, dass das Material nicht die äußeren Flächen der Arbeit berührt.

Setzen Sie nun Ihr Objekt auf den Haltestift oder direkt auf Ihren Brenngutträger (hierzu einen kleinen Überschuss in die Krone füllen). Eine Trocknungszeit ist nicht einzuhalten. Führen Sie nun wie gewohnt den Brennvorgang durch, für den Gebrauch von DD contrast® firing paste wird keine Temperaturanpassung des Brennvorgangs benötigt.

Nach dem Brand entfernen Sie DD contrast® firing paste ganz einfach durch einen gezielten Druckluftstoß rückstandslos. Bitte brennen Sie die DD contrast® firing paste nur einmal. Da das Material leicht kontrahiert, ist bei wiederholten Brennvorgängen der perfekte Halt des Brennguts nicht garantiert.

DD contrast® firing paste enthält kleine Fasern, die unter Umständen den Spritzenkanal blockieren können – bitte einfach mit einem Instrument den Spritzenkanal wieder befreien.

Die Verschlusskappe der Spritze bitte direkt nach Gebrauch wieder aufschrauben, um ein Austrocknen des Materials zu verhindern!

Properties:

DD contrast® firing paste – the ultimate Ceramic Firing Paste – Peg Putty

- Conveniently stabilizes ceramic restorations on firing pegs.
- Zero clean-up is required – just a blast of compressed air is sufficient.
- No tiresome divesting by way of scraping out and sand blasting.
- No drying time is required.

Directions for use:

Apply a small amount from the sirynge directly into the crown/coping or on the back of the veneer or inlay. Please make sure that the material does not touch the visible surfaces of the ceramic.

Fix and adjust your object on the holding pins of the firing tray or place it directly on the tray (please fill the coping with a little excess material to do so). No drying time is required. The last step is to start your firing process as usually, DD contrast® firing paste does not require any adjustments of the firing cicle. After Firing simply clean off DD contrast® firing paste with a purposeful stroke of compressed air. Please do not reuse the DD contrast® firing paste once fired because the material contracts a bit and a perfect fit during further firing cicles cannot be guaranteed.

DD contrast® firing paste contains small fibres that might clogg the sirynge tip – please simply use an instrument to unclogg the tip again.

The sealing cap of the sirynge has to be put on immediately after usage in order to prevent a dry out of the material!

Rev. 01_2019/10

Dental Direkt GmbH | Tel: +49 5225 86319-0
E-Mail: info@dentaldirekt.de | www.dentaldirekt.de